

VeriShield® V250

HIGH-DENSITY MODULAR RADIATION SHIELDING



VeriShield radiation shielding components are individual modules combined together to form a composite structure to create the required radiation attenuating environment. The constructed system retains the ability to be deconstructed and reused.

VeriShield products are manufactured in a controlled environment and incorporate high Z aggregates (for photon attenuation) as well as neutron additive materials.

The VeriShield photon, neutron and electron shielding modules feature a design that presents a full 100% inter-locking edge. Lapping or alternating of the seams results in the prevention of straight line paths for radiation streaming. Modules interlock together to form a solid and stable structure.

Standard VeriShield V250 modules are $5" \times 5" \times 10"$ (127 x 127 x 254mm). Verishield V250 is also available in half thickness, with a nominal thickness of 2.5" (63 mm).

5" (127mm)

10" (254mm)

10.75" (273mm)

Compressive strength is guaranteed to meet 5,200 psi. This product routinely easily surpasses this minimum and is typically on the order of 6,000 psi and above (depending upon final mix ratios). Grout materials will have a lesser compressive strength as water content is increased for working properties, but shall not be less than 5,000 psi when mixed on site.

Veritas VeriShield® V250 and VeriShield Grout

VeriShield V250 Shielding Modules and High Density Grout are manufactured and packaged in a controlled environment and incorporate high Z aggregates (for photon attenuation) as well as neutron additive materials.

Designed to be mixed with portland cement, VeriShield Grout will remain volume stable in both wet and dry conditions, and remains stable without cracking or lamination from compressive loading, impact, lateral thrust, high heat or continuous vibration.



SIZE	5" x 5" x 10" – 127 x 127 x 254mm
WEIGHT PER MODULE	36 lbs – 16.4 kg
DENSITY	250 lbs/cu ft – 4 g/cu. cm (median)
COMPRESSIVE STRENGTH	5,200 psi - 366 kgf/cm2
SOLUBILITY	Insoluble
REACTIVITY	Non-Reactive
MELTING POINT	^2,800°F - 1,538°C
BOILING POINT	N/A

Grout compressive strength shall never be less than 5,000 psi when mixed on site.

COMPOSITION INFORMATION

Major Compounds
Chemical Name

Chemical Name
Portland Cement
Gypsum (calcium sulfate)

* May contain crystalline silica

CAS Registry Number
*65997-15-1
13397-24-5

* May contain crystalline silica

PHYSICAL/CHEMICAL CHARACTERISTICS

Boiling Point N/A
Vapor Pressure (mm Hg) N/A
Melting Point N/A
Vapor Density (AIR-1) N/A
Evaporation Rate N/A
Solubility in Water N/A
Appearance & Odor Grey; no odor

FIRE AND EXPLOSION HAZARD DATA - NONE

REACTIVITY DATA

Stability: Stable



RADIATION ATTENUATION

Attenuation is based on interpolated data for some energies. The listed TVL's represent the average tenth value thickness after 5 decades of attenuation. First TVT and equilibrium TVL's may be available for thin barrier sections.

Veritas will provide calculations with appropriate safety factors to ensure attenuation requirements are met.

V250 Attenuation - Primary Barrier (1TVL=)

6MV:	8.3" - 21.0 cm
10MV:	9.4" - 23.8 cm
15MV:	10.4" - 26.5 cm
18MV:	10.7" - 27.2 cm

V250 Attenuation - Secondary Barrier (1TVL=)

6MV: 6.7" - 17.1 cm 10MV: 7.4" - 18.7 cm 15MV: 8.0" - 20.2 cm 18MV: 8.0" - 20.2 cm



